



aplicaRev Top

WATERPROOF WHITE RENDERING MORTAR

Impermeable white rendering and finishing mortar for use on façades.
 Spray-on mortar for indoor and outdoor use.
 GP-CS IV - W2 in accordance with Standard UNE-EN 998-1.

- Multi-finish
- Apply manually or mechanically
- Semi-light

DESCRIPTION

Mortar made with white Portland cement, screened aggregate of controlled grain size, and additives which improve the product's workability, adhesion and plasticity. Machine mixable.

APPLICATION SURFACES

The surfaces must be rough, hard, stable, clean, and free from dust, paint and release agents.

Check that the application surface is suitably flat and that no areas are prone to disintegration. If required, fix the surface 24 hours beforehand, filling any holes with the same material. Brickwork, concrete blocks, thermo-clay, rough M-7.5 mortar renderings and concrete.

INSTRUCTIONS FOR USE



- 1 Check that the surface is suitable and ready for use.
- 2 Moisten the application surfaces before use.
- 3 Mix with 5.5 – 5.8 litres of clean water per sack using an electric mixer at low rpm until you obtain a smooth, lumpfree paste of the required consistency.
- 4 Leave the paste to stand for 2 minutes and mix again before applying.
- 5 Spread over the application surface to a thickness of no more than 5 mm.
- 6 Once the paste has started to harden, smooth the surface with a wooden or plastic trowel.
- 7 After 24 hours, moisten the mortar. Repeat this process for 2 or 3 days.

APPLICATIONS

General purpose white finishing mortar for use on patios, dividing walls, garages, fences, thoroughfares.

WARNINGS AND RECOMMENDATIONS

- Do not apply onto plaster.
- Do not apply this product when frost or rain are forecasted.
- Do not apply at temperatures below 5°C or above 35°C.
- For thicknesses greater than 20 mm, apply in two coats, leaving at least 24 hours between each one.
- It is advisable to moisten absorbent or very hot surfaces before applying the product and 24 hours afterwards in order to prevent the mortar from becoming overly dry or less strong.
- Do not apply onto waterproofed surfaces.
- If applying to smooth or non-porous surfaces or concrete, use **aplicaRev Fix** as an adhesive bridge.
- This product is ready to use mixed with water. Do not add any kind of additional substance which may alter its properties.
- Use within 1 year of date of packaging. Store the product in its original sealed packaging in a dry, covered place protected from humidity.

aplicaRev Top

WATERPROOF WHITE RENDERING MORTAR



AVAILABLE FORMATS

aplicaRev Top is available in 25 kg paper sacks with moisture-proof plastic lining, dispatched on shrink-wrapped pallets weighing a total of 1,600 kg (64 sacks).

TECHNICAL FEATURES

| | |
|------------------------------|--|
| Mixing water | 5,5 - 5,8 l/sack |
| Compressive strength | > 5 N/mm ² |
| Flexural strength | > 1,7 N/mm ² |
| Adhesive strength | > 0,4 N/mm ² |
| Capillary action | < 0,2 Kg/m ² min ^{0,5} |
| Mortar density once hardened | 1,45 ± 0,1 Kg/l |
| Shrinkage | < 0,5 mm/m |
| Grain size | < 1,5 mm |
| Chloride content | < 0,01 % |
| Consumption | 13±2 Kg/m ² per cm |

NOTE

The recommendations for use are based on our own knowledge and experience. The technical data provided have been obtained under normal laboratory conditions, and may therefore vary according to the environmental conditions in the place where the product is used. As the application conditions are beyond our control, the information provided here does not imply that the company accepts responsibility for any variations.