

- Easy workability
- White and grey
- Apply manually or mechanically



Capa Projectable

SPECIAL MACHINE-SPRAYABLE COVERING MORTAR

Rendering and finishing mortar. Grey or white. For indoor and outdoor use. GP-CR-CS III – W2 in accordance with Standard UNE-EN 998-1.

DESCRIPTION

Mortar made with white Portland cement, with inorganic pigments, screened aggregate of controlled grain size, and additives which improve the product's workability, adhesion and plasticity.

Specially-formulated to be sprayed on using a machine.

APPLICATIONS

General-purpose rendering and finishing mortar for use on façades, patios, garages, fences, dividing walls.

APPLICATION SURFACES

The surfaces must be rough, hard, stable, clean, and free from dust, paint and release agents.

Check that the application surface is suitably flat and that no areas are prone to disintegration. If required, fix the surface 24 hours beforehand, filling any holes with the same material. Brickwork, concrete blocks, thermo-clay, rough M-7.5 mortar renderings and concrete.

WARNINGS AND RECOMMENDATIONS

- Do not apply onto plaster.
- Do not apply this product when frost or rain are forecasted.
- Do not apply at temperatures below 5°C or above 35°C.
- For thicknesses greater than 15 mm, apply in two coats, leaving at least 24 hours between each one.
- It is advisable to moisten absorbent or very hot surfaces before applying the product and 24 hours afterwards in order to prevent the mortar from becoming overly dry or less strong.
- Do not apply onto waterproofed surfaces.
- If applying to smooth or non-porous surfaces or concrete, use **Capafix** as an adhesive bridge.
- This product is ready to mix with water. Do not add any kind of additional substance which may alter its properties.
- Use within 1 year of date of packaging. Store the product in its original sealed packaging in a dry, covered place protected from humidity.

INSTRUCTIONS FOR USE



- 1 It is better to apply this product with a machine.
- 2 Mix gradually with 4.7 – 5 litres of clean water per sack until you obtain a smooth, lump-free paste of the required consistency.
- 3 Spread evenly over the application surface, covering with a maximum thickness of 15 mm.
- 4 After approximately 30 minutes (depending on the weather conditions), trowel with a plastic or wooden float.

Capa Proyectable

SPECIAL MACHINE-SPRAYABLE COVERING MORTAR



AVAILABLE FORMATS

Capa Proyectable is available in 25 kg paper sacks with moisture-proof plastic lining, dispatched on shrink-wrapped pallets weighing a total of 1,000 kg (40 sacks).

TECHNICAL FEATURES

Mixing water	4,75- 5 l/sack
Compressive strength	> 5 N/mm ²
Flexural strength	> 1,7 N/mm ²
Adhesive strength	> 0,3 N/mm ²
Mortar density once hardened	1,45 ± 1 Kg/l
Shrinkage	< 1 mm/m
Grain size	< 1,6 mm
Chloride content	< 0,01 %
Consumption	22±2 Kg/m ²

NOTE

The recommendations for use are based on our own knowledge and experience. The technical data provided have been obtained under normal laboratory conditions, and may therefore vary according to the environmental conditions in the place where the product is used. As the application conditions are beyond our control, the information provided here does not imply that the company accepts responsibility for any variations.