



Capasec Color

MASONRY CEMENT MORTAR

General purpose industrial masonry mortar

- Class: M-7.5
- Masonry mortar

DESCRIPTION

Mortar made with white or grey Portland cement, aggregate of controlled grain size, and additives which improve the product's workability and plasticity. General purpose masonry mortar (G), in accordance with UNE-EN 998-2.

APPLICATIONS

Masonry factories (façades, exterior walls, pillars, partitions), grouting and laying ceramic bricks, concrete blocks, stonework. General masonry works.

INSTRUCTIONS FOR USE



- 1 The surfaces must be rough, hard, stable, clean, and free from dust, paint and release agents. The surface must be free from any foreign substances.
- 2 Mix with 3,3 litres of clean water per sack using an electric mixer at low rpm. Add the water gradually until you obtain a smooth, lump-free paste of the required consistency.
- 3 Leave the paste to stand for 2 minutes and mix again before applying.

WARNINGS AND RECOMMENDATIONS

- Do not apply onto plaster.
- Do not apply this product when rain is forecasted.
- The aggregate applied must be dry.
- Do not apply at temperatures below 5°C or above 35°C.
- Apply two coats for thicknesses greater than 15 mm.
- It is advisable to moisten absorbent or very hot surfaces before applying the product and 24 hours afterwards in order to prevent the mortar from becoming overly dry or less strong.
- This product is ready to mix with water. Do not add any kind of additional substance which may alter its properties.
- To increase the impermeability and adhesion, mix with a litre of **aplica Latex** per sack of mortar.
- Use within 1 year of packaging date. Store the product in its original sealed packaging in a dry, covered place protected from humidity.
- For **aplicaSec Gris**, due to its composition, consistency in the color of the mortar is not guaranteed.

Capasec Color

MASONRY CEMENT MORTAR

AVAILABLE FORMATS

Capasec Color is available in 25 kg paper sacks with moisture-proof plastic lining, dispatched on shrink-wrapped pallets weighing a total of 1,600 kg (64 sacks).



TECHNICAL FEATURES

M-7.5

Mixing water	3,2 - 3,4 l/sack
Compressive strength	> 7,5 M/mm ²
Flexural strength	> 7,5 M/mm ²
Mortar resistance once hardened	1,85 ± 0,1 Kg/l
Shrinkage	< 2 mm/m
Grain size	< 2 mm
Chloride content	0,01 %

NOTE

The recommendations for use are based on our own knowledge and experience. The technical data provided have been obtained under normal laboratory conditions, and may therefore vary according to the environmental conditions in the place where the product is used. As the application conditions are beyond our control, the information provided here does not imply that the company accepts responsibility for any variations.