

APLICACOLOR

0-15

DEFORMABLE MORTAR FOR 0-15 mm JOINTS

Deformable, waterproof, very fine cement-based mortar for the rendering and grouting of tiled walls and floors. Classified as CG2 WA according to UNE EN 13888.



Waterproof



Easy to apply



30 colours



For indoor and outdoor use



CG2 WA

DESCRIPTION

Portland cement mortar with special additives and resistant inorganic pigments, used to fill joints 0 - 15 mm wide. aplica Color 0-15 is suitable for filling joints between any ceramic and natural stone tiles. For indoor and outdoor use. Waterproof.

WARNINGS AND RECOMMENDATIONS

Do not apply at temperatures below 5°C or above 35°C.

Do not apply when frost or rain are forecasted.

Avoid applying when direct sunlight is shining on the application surface.

Always use the exact required amount of water.

For joints exceeding 15 mm in width or depth, add 4 litres of aplica Latex per 20 kg bag and 1 litre per 5Kg bag and fill with water until optimal consistency.

INSTRUCTIONS FOR USE

1. Mix mechanically with clean water until you obtain a smooth paste of the required consistency.
2. Leave to stand for 2 - 5 minutes before applying.
3. Check that joints are clean and free from any dust or adhesive.
4. Moisten the application surface if weather conditions require it.
5. Fill each joint with paste using a rubber trowel. Carry out the finishing process once the top of the mortar has started to harden.



APLICACOLOR 0-15

Rev - 07/2025

AVAILABLE FORMATS

aplica Color 0-15 is presented in 20 kg paper sacks on 960 kg pallets (48 sacks). Use within 2 years of the packaging date. Store the product in its original sealed packaging in a dry, covered place, protected from moisture.

TECHNICAL FEATURES

Appearance	Pre-mixed powder
Mixing water	6.4 liters per 20 Kg bag
Paste density	1,80 ± 0,05 Kg/l
Compressive strength 28 days after application	>25 N/mm ²
Flexural strength 28 days after application	>5 N/mm ²
VOCs	A N° 18/17198-1381
Paste life at 20°C	>60min
Shrinkage	<1 mm/m
Classification according to Standard UNE-EN 13888	CG2 WA

**The colors are indicative and may undergo slight modifications because they are natural elements. Please make a physical sample of the selected color for final validation.*

YIELD FIGURES : KG/M²

R= 1,82 x Z x H x (10/Z + 10/Y).

R= Yield: kg/m²

Z: Joint Width in cm

H: Joint Depth in cm

X: Tile Width in cm

Y: Tile Length in cm

1.82: Paste density (kg/l)

NOTE

The recommendations for use are based on our own knowledge and experience. The technical data provided have been obtained under normal laboratory conditions, and may therefore vary according to the environmental conditions in the place where the product is used. As the application conditions are beyond our control, the information provided here does not imply that the company accepts responsibility for any variations.